

Technisches Datenblatt

2313 2007

Additiv zum verhindern der Kristallstruktur bei Stearinkerzen

Verwendungszweck:

Um Kristallbildung von Stearinsäure zu unterdrücken
Bei Stearinkerzen, deren Oberfläche nicht die typische Kristallstruktur von Stearin aufweisen, sondern glatt sein soll.

Dichte:

0,98g / cm³

Schmelzpunkt:

70°C – 75°C

Verarbeitung:

Empfohlene Dosierung: 0,1 – 0,2%

Einarbeitung bei 80°C mit ausreichender Rührvorrichtung.

Verpackung / Lagerung:

Pastillenform
in Plastik-Eimer á 5 kg oder á 10 kg
in Säcken á 20/25 kg
Großkarton auf Palette á 500 kg

Das Produkt ist bei Raumtemperatur und trocken zu lagern.

Sicherheitshinweise:

Das Produkt ist nach der Verordnung über gefährliche Stoffe (GefStoffV) nicht kennzeichnungspflichtig.

Wichtig:

Die Angaben dieses Datenblattes basieren auf unseren derzeitigen Kenntnissen und Erfahrungen. Sie befreien den Verarbeiter wegen der Fülle der möglichen Einflüsse bei Verarbeitung und Anwendung unseres Produktes nicht von eigenen Prüfungen und Versuchen. Diese Versuche sollten möglichst vor einer großen Produktionsmenge durchgeführt werden!

Technical Data Sheet

2313 2007

additive to prevent the crystal structure at stearin candles

Purpose:

To suppress crystal formation of stearic acid.
When stearin, whose surface does not have the typical Kristallstruktur of stearin, but should be smooth.

Density:

0,98g / cm³

Melting point:

70°C – 75°C

Processing:

Recommendad dosage: 0.1 – 0.2%.

Incorporation of at 80°C with sufficient stirring.

Packing / Storage:

Pastilles
in plastic buckets á 5 kg or á 10 kg
in sacks á 20/25 kg
Large carton on pallet á 500 kg

The product should be stored dry at room temperature.

Safety advice:

The product is not subject to classification according to the regulation on hazardous substances (Ordinance on Hazardous Substances).

Important:

The general information of this datasheet is based upon our current knowledge and experience. Because of plenty of possible influences during processing our product they can not deliver the processor from its own testing and controlling. These trials should be made before the lacquer system will be used in production!