



Product data sheet

1 / 1

Product name **TUDASTAR 5405**
Customer product designation
Issue / Version 1 / 2026-04-30

Typical product data

Analysis	Method	Unit	Typical
Density 80 °C	DIN EN ISO 12185	kg/m ³	772,0
Congealing Point	DIN ISO 2207	°C	57,0
Colour Saybolt	ASTM D6045	-	30
Needle penetration 25 °C	DIN 51579	mm/10	18
Content of oil	DIN 51531	Mass.-%	0,4
Purity	BfR recommendation XXV		confrom
Purity	Latest Edition Ph. Eur.		confrom
Kin. Viscosity 100 °C	DIN EN ISO 3104	mm ² /s	4,200

The above mentioned data are only an indication and do not represent any guarantee. Any deviations of the data are no reason for claim.



DIN EN ISO 9001
DIN EN ISO 14001*
DIN EN ISO 45001*
DIN EN ISO 50001**
DIN EN ISO/IEC 17025**

Headquarters:
H&R Group
Am Sandtorkai 64
20457 Hamburg, Germany
Phone +49 40 43218-0
Fax +49 40 43218-400
Internet www.hur.com

Mineral oil and vaseline plant:
Tudapetrol Mineralölerzeugnisse
Nils Hansen GmbH & Co. KG*
Halskestraße 30-34
22113 Hamburg, Germany
Phone +49 40 781108-0
Fax +49 40 781108-199

Refinery Salzbergen:
H&R ChemPharm GmbH*, **
Neuenkirchener Straße 8
48499 Salzbergen, Germany
Phone +49 5976 945-0
Fax +49 5976 945-624

Refinery Hamburg:
H&R Ölwerke Schindler GmbH*, **
Neuhöfer Brückenstr. 127-152
21107 Hamburg, Germany
Phone +49 40 32523-0
Fax +49 40 32523-285